



Creative Textstyles bvba
Mevr. Nancy Vanelverdinghe
Wijnendalestraat 178
8800 ROESELARE

Your notice of
17-05-2019

Your reference

Date
29-05-2019

Analysis Report 19.03010.01


Required tests :
AATCC 148 (2014)

Determination of the light permeability-Black box

Identification number	Information given by the client	Date of receipt
T1911104	Texture	17-05-2019

Els Vantomme
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T1911104 - Texture

Determination of the light permeability-Black box

Date of ending the test 28-05-2019
 Standard used AATCC 148 (2014)

Apparatus Lightning source, test box and lux meter

Results

Blank luminous intensity in lux 1000

	Lux value					Light permeability
	1	2	3	4	5	%
T1911104	3.8	3.0	3.2	3.1	3.2	0.33